

Shenzhen Petra Industrial Co., Ltd.

Self-adhesive product manual

Product Code	HF9026			
Product Name	65g topcoated thermal paper film/water base adhesive/60g white glassine			
Face Stock	65g topcoated thermal paper film			
Release liner	60g white glassine			
Adhesive	Ordinary water base adhesive			
technical indicators:				
Classification:	test project	Indicators	Unit	Methods
Face Stock	Dosage	$65\pm 10\%$	g/m ²	GB/T 451.2-2002
	Thickness	$75\pm 10\%$	μm	GB/T 451.3-2002
	Whiteness	$\geq 80\%$	%	GB/T 7974-2002
	waterproof	$\geq 60\%$	%	GB/T 28210-2011
	oilproof	$\geq 70\%$	%	GB/T 28210-2011
	alcohol resistance	$\geq 60\%$	%	GB/T 28210-2011
	chromatic optical density	≥ 1.0	%	GB/T 28210-2011
Release liner	Dosage	$60\pm 10\%$	g/m ²	GB/T 451.2-2002
	Thickness	$53\pm 10\%$	μm	GB/T 451.3-2002
	Longitudinal tensile strength	$\geq 5.0\text{KN/m}$	KN/m	GB/T 12914-2018
Adhesive	Loop initial tack	≥ 8	N	FTM9
	90° release force	≥ 5	N/25mm	FTM2
	180° 30m/min high speed release force	$\geq 35\text{g}$	g/m ²	FTM1
	Holding power	$\geq 8\text{hours}$	/	GB/T 4851-2014
	Minimum labelled temperature	10℃		
Using temperature	-15℃~65℃			
Product description:	It is produced with high quality raw materials, with high Whiteness, clear printing, excellent waterproof, oilproof, alcohol resistance, high temperature resistance, and good thermal image preservation performance.			
Print and process:	Can be used for printing in most traditional printing methods. Due to the heat-sensitive nature of the product, processing environments exceeding 50° C should be avoided. Inks containing alcohol or volatile organic solvents may damage the heat-sensitive layer. For flexographic printing, UV or water-based ink and varnish are recommended. It is recommended to test the ink before printing. It can be used for non-direct contact labeling of products such as food, medicine and cosmetics.			
Stock and preserve:	Avoid long-term exposure to environments above 50° C or direct sunlight. Under the conditions of temperature $23\pm 2^\circ\text{C}$ and relative humidity $50\pm 5\%$, the validity period is 1 year. Products beyond the expiry date can still be used after passing the inspection.			

Special Note:

1. Since the product is closely related to the use environment and production and processing technology, please test before use, and re-test when changing seasons to avoid unknown risks.
2. All material descriptions, technical information and usage recommendations of Petralabel are test data in a standard environment, but they are not guaranteed, and there may be differences in actual application data.
3. The technical documents are subject to the current terms of Yangfan, and petralabel reserves the right of final interpretation. Shenzhen Petra Industrial Co., Ltd.

Address: Room 1403-1404, Building 1, Longguang

Century Building, Xin'an Street, Bao'an District, Shenzhen

URL: www.Petralabel.cn

E-mail: Jessie@petralabel.com