

Shenzhen Petra Industrial Co., Ltd.

Self-adhesive product manual

| | | | | |
|-----------------------|--|-----------------------|------------------|-----------------|
| Product Code | LB2802 | | | |
| Product Name | 70g woodfree paper/freezing glue/60g yellow glassine | | | |
| Face Stock | 70g woodfree paper | | | |
| Release liner | 60g yellow glassine | | | |
| Adhesive | freezing glue | | | |
| technical indicators: | | | | |
| Classification: | test project | Indicators | Unit | Methods |
| Face Stock | Dosage | 70±10% | g/m ² | GB/T 451.2-2002 |
| | Thickness | 88±10% | μm | GB/T 451.3-2002 |
| | Whiteness | ≧85% | % | GB/T 7974-2002 |
| Release liner | Dosage | 60±10% | g/m ² | GB/T 451.2-2002 |
| | Thickness | 53±10% | μm | GB/T 451.3-2002 |
| | Longitudinal tensile strength | ≥5.0KN/m | KN/m | GB/T 12914-2018 |
| Adhesive | Loop initial tack | ≧12 | N | FTM9 |
| | 90° release force | ≧6or paper torn state | N/25mm | FTM2 |
| | 180° 30m/min high speed release force | ≧35g | g/m ² | FTM1 |
| | Minimum labelled temperature | - 5℃ | | |
| | Using temperature | - 15℃~65℃ | | |
| Product description: | Face Stock is made of high quality woodfree paper, which has good processing performance and is suitable for writing and printing; before use, a comprehensive labeling test is required in the final use environment. | | | |
| Print and process: | Face Stock has good ink absorption and can be used for color printing and inkjet printing on general rolls and sheet-fed paper. Suitable for making all kinds of low glossiness labels, price labels, etc. | | | |
| Stock and preserve: | Under the conditions of temperature 23±2℃ and relative humidity 50±5%, the validity period is 1 year. Products beyond the expiry date can still be used after passing the inspection. | | | |

Special Note:

1. Since the product is closely related to the use environment and production and processing technology, please test before use, and re-test when changing seasons to avoid unknown risks.
2. All material descriptions, technical information and usage recommendations of Petralabel are test data in a standard environment, but they are not guaranteed, and there may be differences in actual application data.
3. The technical documents are subject to the current terms of Yangfan, and petralabel reserves the right of final interpretation. Shenzhen Petra Industrial Co., Ltd.

Address: Room 1403-1404, Building 1, Longguang Century Building, Xin'an Street, Bao'an District, Shenzhen

URL: www.Petralabel.cn

E-mail: Jessie@petralabel.com