

Shenzhen Petra Industrial Co., Ltd.

Self-adhesive product manual

Product Code		SN7560		
Product Name		75g topcoated thermal paper/hot melt adhesive/60g white glassine		
Face Stock		75g topcoated thermal paper		
Release liner		60g white glassine		
Adhesive		Ordinary hot melt adhesive		
technical indicators:				
Classification:	test project	Indicators	Unit	Methods
Face Stock	Dosage	75±10%	g/m ²	GB/T 451.2-2002
	Thickness	85±10%	μm	GB/T 451.3-2002
	Whiteness	≧80%	%	GB/T 7974-2002
	waterproof	≧60%	%	GB/T 28210-2011
	oilproof	≧70%	%	GB/T 28210-2011
	alcohol resistance	≧60%	%	GB/T 28210-2011
	耐高温	≧90	℃	FTM1
	chromatic optical density	≥1.20	%	GB/T 28210-2011
Release liner	Dosage	60±10%	g/m ²	GB/T 451.2-2002
	Thickness	53±10%	μm	GB/T 451.3-2002
	Longitudinal tensile strength	≥5.0KN/m	KN/m	GB/T 12914-2018
Adhesive	Loop initial tack	≧14	N	FTM9
	90° release force	≧7or paper torn state	N/25mm	FTM2
	180° 30m/min high speed release force	≧35g	g/m ²	FTM1
	Minimum labelled temperature	10℃		
	Using temperature	-15℃~65℃		
Product description:		This product adopts Ordinary hot melt adhesive, heat-sensitive Face Stock has excellent waterproof, oilproof, alcohol resistance, high temperature resistance effect, does not consume ink or toner, and prints clearly.		
Print and process:		Can be used for printing in most traditional printing methods. Due to the heat-sensitive nature of the product, processing environments exceeding 50° C should be avoided. Inks containing alcohol or volatile organic solvents may damage the heat-sensitive layer. For flexographic printing, UV or water-based ink and varnish are recommended. It is recommended to test the ink before printing. This product has strong high temperature resistance and can be used for non-direct contact labeling of food, medicine and cosmetics.		
Stock and preserve:		Avoid long-term exposure to environments above 50° C or direct sunlight. Under the conditions of temperature 23±2℃ and relative humidity 50±5%, the validity period is 1 year. Products beyond the expiry date can still be used after passing the inspection.		

Special Note:

1. Since the product is closely related to the use environment and production and processing technology, please test before use, and re-test when changing seasons to avoid unknown risks.
2. All material descriptions, technical information and usage recommendations of Petralabel are test data in a standard environment, but they are not guaranteed, and there may be differences in actual application data.
3. The technical documents are subject to the current terms of Yangfan, and petralabel reserves the right of final interpretation.

Shenzhen Petra Industrial Co., Ltd.

Address: Room 1403-1404, Building 1, Longguang

Century Building, Xin'an Street, Bao'an District, Shenzhen

URL: www.Petralabel.cn

E-mail: Jessie@petralabel.com